



Science Arena Publications
Specialty Journal of Engineering and Applied Science

ISSN: 2520-5943

Available online at www.sciarena.com

2018, Vol, 3 (1): 19-29

Effect of Increase of Current Intensity on Creating Possibility of TIG Soldering Speed in Aluminum Alloy to Steel Connection

Mousavifar, S.A., Bani Mostafa Arab, N.*

Faculty of Mechanic Engineering, Shahid Rajaei University, Tehran, Iran.

*Corresponding Author

Abstract: According to this matter that the connection of diverse metals such as AL 5A06 with 660° melting point and steel SU 321 with 1385° melting point with different thermal features like the expansion coefficient and conductivity for the connection in the fusion welding conditions causes the creation of internal pressure after the welding. Then, the connection of these two kinds of metal, despite its necessity and specific application by the fusing method, would be resulted in considerable breakdown and impairments; so, the method of soldering (arc welding) was applied with inert Argon-based shielding and with Pulse TIG machine with developed technology and application of cover of plating Zn on SU 321 and producing the galvanized steel on the steel SU 321 and for the reason of increase of the speed of soldering operations with being lower of the current intensity, the formation of the tiny fines at lower surfaces of the weld pool would be faced with difficulty. So, for the increase of formation of tiny fines instead of coarse fines, the progressive increase of current strength according to the increase of soldering speed is one of the factors of formation of the tiny fines. So, it can be said that the current intensity is a factor effective on providing the condition for creating the TIG soldering speed in the connection of AL 5A06 and SU 321.

Taxonomy:

Galvanization: cover of aluminum on steel, AL 5A06: aluminum alloy

Progressive increase: staircase increase, SU 321: stainless steel, Pulse: pulsed.

Keywords: Increase of Current, Possibility of TIG Soldering, Speed in Aluminum

INTRODUCTION

The necessity of the connection of similar and diverse metals to each other has been of observable subjects of today and has special status among the industries; and always many efforts have been made to achieve the technology of metals connection (A. S. M, 1976). Among different kinds of connections, the special attention has been paid to the weld connections because of their resistance and the product of these efforts is the variety of welding. Among different welding methods with developed technology, special attention has been paid to the connection of diverse metals by welding in the industries specially the industries of aerospace and projectile, and the industries of topography in making the very exact digital cameras and the exhaust manifold and connecting the cylinder head to the leg of injectors and dynamo and dashboard; and for this purpose, it was decided to weld the diverse metal of aluminum to the galvanized steel because of different reasons such as different melt temperature and expansion coefficient and high wettability at melt temperature of AL in soldering operations by the welding Pulse TIG machines (A. Althouse et al., 1984; H. W.

Pollack, 1988). With regard to the literature review of research, many studies was done in 2009 by the researchers of this industry like J.L.S, C.B.L, C.L.F, S.B.A, J.L, G.C, and L.Y; and these studies were carried out in regard of the connection of two diverse metals Aluminum Alloy and galvanized Steel by the use of Pulse TIG machines with different features such as " connection of two diverse metals in different conditions", "suitable wettability of galvanized matter", "expansion of cable of welding the liquid aluminum on the surfaces of steel", " increase of efficiency and application of inert Argon in this soldering and protection of proper mechanical features of the matters in different conditions of speed of welding operations" ; that in this welding, the most important parameters such as the increase of gas flow rate are considerable(Moeinian 1st volume, 2006; Moeinian 3rd volume, 2006; Moeinian second volume, 2006). The gas flow rate is one of the most effective factors in the protection of connection quality at high speed and because, in literature review of the research, this kind of connection has been studied in the operations with high speed; so, this parameter was studied in this research due to its effect on the speed of operations of diverse metals connection (V. Muthupandi et al., 2003).




Figure 1: Manner of preparation of segments for welding




Figure 2: Manner of preparation of fixed segments for welding

Table 1: Features of TIG welding machine- Model 200PARSTIG AC/DC 200

200	Current maximum with lowest work factor
5- 200	Current welding of DC ampere
5- 200	Current welding of AC ampere
200	Current welding with work factor of %35
120	Current welding with work factor of %60
85	Amount of DC voltage
70	Amount of AC voltage
Current balance, manual phase of low amplitude of gas	Modulation

HF	Ignition system
Sinuuous form	Wavy forms



Figure 3: Look of segment of SU 321 tested for the analysis of chemical compound

Table 2: Result of testing the tensile of segment of SU 321 for evaluating its resistance

Row	Thickness*width A*B (mm*mm)	Cross-sectional area S0 (mm ²)	Resistance proof of offset Rt 0.2% Mpa	Final resistance of Rm Mpa	Elongation
1	12.58*2.97	37.36	382	609	47
Uncertainty of UE= +/-3%					
Standard permissible limit					

Table 3: Results of analysis of chemical compound of SU 321 sheet (weight percent)

C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu
0.033	0.57	1.21	0.015	<0.003	17.1	0.09	9.1	0.019	0.01	1.09
Nb	Ti	V	W	Fe						
0.017	0.38	0.10	<0.02	Base						




Figure 4: Look of segment of untested Al-5106

Table 4: Results of testing the tensile of segment of Al-5A06 for evaluating its resistance

row	Thickness*width A*B (mm*mm)	Cross-sectional area S ₀ (mm ²)	Resistance proof of offset Rt 0.2% Mpa	Final resistance of R _m Mpa	Elongation
-----	-----------------------------------	---	---	---	------------

1	12.55*3.0	36.65	146	311	24.5
Uncertainty of $U_E = \pm 3\%$					
Standard permissible limit					

Table 5: Results of analysis of chemical compound of Al 5A06 plate (weight percent)

Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Be	Ca	Li
0.16	0.29	0.06	0.8	4.25	0.08	0.02	0.03	0.033	Trace	Trace	Trace
Pb	Sn	Sr	V	Na	Bi	Co	Zr	B	Gx	Cd	Al
0.01	<0.005	Trace	0.013	Trace	0.002	0.003	Trace	0.003	0.003	0.004	Base

Table 6: Comparison of compounds of segments and filler

row	materials	Al percent	Fe percent	Si percent	Zn percent	Explanation
1	Al 5a06	Base	0.29	0.16	0.03	The mount of mentioned percent of aluminum exists in the segment.
2	SU 321	0.019	Base	0.57	-	The aluminum with galvanized cover or No Clock Flux is provided.
3	Al Si 4047	Rem	0.35	0.3-0.6	<0.05	The mount of mentioned percent of aluminum exists in the segment.

Table 7: Current intensity at different welding speeds

Soldering speed (s)	80mm/s	100mm/s	120mm/s	165mm/s
Current intensity (I)	45A	55A	65A	100A

Procedure

In the connection of these two diverse metals, a segment of stainless steel SU 321 with dimensions of 120mm×50mm×3mm and slat angle of 45° and melting point of 1385° and a segment of Aluminum Alloy with dimensions of 120mm×50mm×3mm in the slat angle of 30° and melting point of 660° and a filler of Al Si 4047 with different diameters of 2mm and 3mm were selected and after plating the stainless steel by the use of Zn and its galvanization for the purpose of assimilating the melting point of steel with the one of Aluminum alloy and providing the condition for the connection and (copper- fastener with dimensions of 130mm×110×10mm and with slope angle of 120mm×8mm×0.5mm for controlling the segments temperature) and with a fixture equipped with two plate fixatives and the tractor including the torch equipped with the speed control systems; and the safety equipment such as crash helmet, gloves, shoes, and specific clothes were prepared. Then, the welding operation was done by the use of inert argon gas with a nozzle with different diameters for the protection of quality of soldering and the Pulse TIG AC- DC – Model 200 Pars welding machine with different speeds were provided for evaluating the possibility of soldering operations with further speed and efficiency; and after machining the welded segments, for doing the tensile and microhardness test operations, the Imstron4208 tensile and Bohler micromet11 microhardness testers were applied respectively for testing the tensile and microhardness of the welded segments (W. F. Hosford & R. M. Caddell, 1983; , Zandi, Y, 2008).




Table 5: Chart of input heat at different welding speeds




Table 6: Chart of gas flow rate at different welding speeds




Table 7: Chart of nozzle diameter at different welding speeds




Table 8: Chart of torch angle with segment surface at different




Table 9: Effect of welding speed on micro hardness of connection




Table 10: Chart of increase of current intensity with different speeds




Table 11: Segment welded from the head with speed of 8 current intensity of 45A and filler of 2mm




Table 12: Segment welded from the head with speed of 10cm/min, current intensity of 55A and filler of 2mm



3 m

Table 13: Segment welded from the head with speed of 16.5cm/min, current intensity of 100A and filler of 3mm



Table 14: Segment welded from the head with speed of 12cm/min, current intensity of 65A and filler

Table 15: Sample of tensile testing of segments with regard to the standard ASTM E8M (2011)



Table 16: Upper look of segment with speed of 8cm/min prepared before tensile test



Table 17: Upper look of segment with speed of 10 cm/min prepared before tensile test



Table 18: Upper look of segment with speed of 12 cm/min prepared before tensile test



Table 19: Upper look of segment with speed of 16 cm/min prepared before tensile test



Table 20: Upper and lower look of segment with speed of 8cm/min prepared after tensile test



Table 21: Upper and lower look of segment with speed of 10 cm/min prepared after tensile test



Table 22: Upper and lower look of segment with speed of 12 cm/min prepared after tensile test



Table 23: Upper and lower look of segment with speed of 16 cm/min prepared after tensile test

Table 8: Results of tensile test with speed of (8 cm/min)

Row	Thickness*width A*B (mm*mm)	Cross- sectional area S ₀ (mm ²)	Resistance proof of offset R _t 0.2% Mpa	Final resistance of R _m Mpa	Place of incidence of break
1	6.11×3.0	18.33	124	150	WM (Weld Metal)

Table 9: Results of tensile test with speed of (10 cm/min)

Row	Thickness*width A*B (mm*mm)	Cross- sectional area S0 (mm ²)	Resistance proof of offset Rt 0.2% Mpa	Final resistance of Rm Mpa	Place of incidence of break
1	6.07×3.0	18.21	122	143	WM (Weld Metal)

Table 10: Results of tensile test with speed of (12 cm/min)

Row	Thickness*width A*B (mm*mm)	Cross- sectional area S0 (mm ²)	Resistance proof of offset Rt 0.2% Mpa	Final resistance of Rm Mpa	Place of incidence of break
1	6.45×3.0	19.35	120	136	WM (Weld Metal)

Table 11: Results of tensile test with speed of (16.5cm/min)

Row	Thickness*width A*B (mm*mm)	Cross- sectional area S0 (mm ²)	Resistance proof of offset Rt 0.2% Mpa	Final resistance of Rm Mpa	Place of incidence of break
1	5.69 ×3.0	17.07	118	129	WM (Weld Metal)




Table 24: Effect of welding speed on final resistance of connection




Table 25: Samples selected for microhardness testing from different weld points



Table 26: Mounted sample of micro hardness testing




Table 27: Chart of amount of micro hardness at welding points with different speeds

Discussion and conclusion

Because the amount of Zn in the segment of Al 5A06 was 0.030% and in the filler of Al Si 4047 was <0.05; but it did not exist in SU 321 segment and for this reason, the melting point of steel is more than the one of AL and their connection is possible only by depressing the melting point of steel by its galvanization. So, by plating Zn on the steel, it was galvanized and by assimilating the melting point of two segments and the use of inert argon gas for the protection of welding quality, the AL 5A05 and SU 321 were connected by the use of welding machine that was most suitable for this connection (Pulse TIG). To access to the further efficiency and output rate, the speed of welding operations was changed from 80mm/s to 165mm/s. That this affair is for the reason of reduction of the heat entered into the lower surfaces of weld pool and also the reduction of fines and the tensile resistance of the connection. For solving this problem, the proper increasing current intensity was applied that was an effective factor in the input heat and also the formation of tiny fines in the weld pool

Reference

1. A. S. M " welding and Brazing of Carbon steels " Book 1 , 2 , 3 1976.

2. A.Althouse , C.Turnquist , W.Bowditch and K.Bowditch , Modern Welding , The Goodheart-Willcox co . , inc . ISBN 0-87006-433-9 , 1984
3. H. W. Pollack , " Materials Science and Metallurgy " Reston , New Jersey , 1988 .
4. Moeinian, M. welding keys, 1st volume, Azade Publications, edited by Nikbakht, M. 2006.
5. Moeinian, M. welding keys, 3rd volume, Azade Publications, edited by Nikbakht, M. 1st edition, 2006.
6. Moeinian, M. welding keys, second volume, Azade Publications, edited by Nikbakht, M. second edition, 2006.
7. V. Muthupandi , P . Bala Srinivasan , SK . Seshadri , S . Sundaresan Effect of weld metal chemistry and heat input on the structure and properties of duplex stainless steel welds . Mater Sci Eng A 2003 ; 358 : 9-16 .
8. W. F. Hosford , R. M. Caddell , " Metal Forming – Mechanics and Metallurgy " , 1983 .
9. Zandi, Y; welding engineering, Forouzesh Publications. Tabriz, 2008.